



## ALMA 65

<b>Classification:</b>	Alumina brick
<b>Main raw materials:</b>	High quality Chamotte - Bauxite
<b>Refractoriness:</b>	>1763 °C
<b>Type of bond:</b>	Ceramic
<b>Features and main applications:</b>	General applications include: steel and cement industries as well as chemical and non-ferrous industries, side walls - rotary kilns and lime kilns.

### Chemical Composition

Al <sub>2</sub> O <sub>3</sub> (%)	SiO <sub>2</sub> (%)	Fe <sub>2</sub> O <sub>3</sub> (%)	TiO <sub>2</sub> (%)
63-67	33-37	< 2.8	< 3

### Properties

<b>Bulk density (g/cm<sup>3</sup>)</b>	2.30-2.45
<b>Cold crushing strength (kg/cm<sup>2</sup>)</b>	450-650
<b>Apparent porosity (%)</b>	16-22
<b>R.U.L (T0.5)( °C)</b>	≈1410
<b>Thermal shock (Cycle in water)</b>	20

ASTM Test Methods, where applicable, used for determination of data.

The above data are typical of the properties of commercial Standard brick.

These data represent average properties obtained from commercial products and should not be considered as guaranteed specifications.

Document code: MRP-SA-FR-11/04

Date of issue: 2025/11/15



[www.mahanrefco.com](http://www.mahanrefco.com)



[info@mahanrefco.com](mailto:info@mahanrefco.com)



+983153309853-4



CONTACT US