



WWW.MAHANREFCO.COM
TECHNICAL INFORMATION

Mahco-Light 1500 LI ***(Castable)***

CHEMICAL ANALYSIS

AL ₂ O ₃ :	40-44	% byWT. (APPROX)
SiO ₂ :	36-40	% ≈
Fe ₂ O ₃ :	<2.5	% ≈
TiO ₂ :	< 4.5	% ≈
CaO:	9-13	% ≈

THERMOMECHANICAL PROPERTIES

	After drying at 110 C°	After heating at 1200 C°
BULK DENSITY :	< 1500 Kg/m ³	
COLD CRUSHING STRENGTH :	2-5 MPa	2-5 MPa
P.L.C :		0 to ± 1.0 %

OTHER PROPERTIES

WATER REQUIRED :	29-36 %
MAX SERVICE TEMPERATURE :	≈ 1280 C°
GRAIN SIZE :	0-5 mm
PACKING :	20 Kg

Note : ASTM, where applicable, used for determination of data.

Factory : Ave. Ayandeh Sazan, Razi Industrial Zone, Isfahan, Iran

Fax : +983153309854

E-Mail: Info@Mahanrefco.com

Sales unit phone : +989139003180 & +989139003186

Date of issue : (Solar Hijri) 1403/02/13

Document code : SA-OT-027/00